



# ECO2 99+ SYNTHETIC DBM (Sintered Magnesia)



<b>DESCRIPTION</b>	ECO2 99+ synthetic DBM is produced from serpentine tailings using patented ECO2 technology. <b>Ultrapure MgO content; Highest bulk density; Totally exempted of boron.</b> Produced with revolutionary CO2 captation technology for lowest emission footprint in the marketplace allowing downstream customers to significantly reduce their carbon footprint.		
<b>USES</b>	For production of high-quality refractory bricks; provides the highest resistance against temperature and corrosion available on the market.		
<b>CHEMICAL COMPOSITION</b>  *Our process makes it possible to adjust the content of this parameter to address customer needs		<b>Typical</b>	<b>Specification</b>
	Magnesium Oxide (MgO), %	98.75	98.3 min.
	*Calcium Oxide (CaO), %	0.55	0.7 max.
	*Silicon Oxide (SiO <sub>2</sub> ), %	0.48	0.6 max.
	*Iron Oxide (Fe <sub>2</sub> O <sub>3</sub> ), %	0.05	0.25 max.
	Aluminum Oxide (Al <sub>2</sub> O <sub>3</sub> ), %	0.05	0.25 max.
	Boron Oxide (B <sub>2</sub> O <sub>3</sub> ), ppm	No Boron	
	Chromium Oxide (Cr <sub>2</sub> O <sub>3</sub> ), %	0.04	
	*CaO:SiO <sub>2</sub> Ratio, wt.	1.15	
<b>PHYSICAL PROPERTIES</b>		<b>Typical</b>	<b>Specification</b>
	Loss On Ignition (LOI), %		0.30 max.
	Bulk Density, (parafin, water method), g/cm <sup>3</sup>	3.51	
	Bulk Density, (mercury method), g/cm <sup>3</sup>	3.53	
<b>PACKAGING</b>	Run-of-kiln briquettes; ECO2 Magnesia offers a variety of packaging options, including bulk (truck and railcar), bags, and bulk sacks. Please contact a sales representative for information.		
<b>STORAGE</b>	Keep away from moisture. Store in a dry place.		

Notice: the information contained herein is, to the best of our knowledge and belief, accurate. Any recommendations or suggestions made are without warranty or guarantee of results since conditions of handling and of use are beyond our control; we therefore, assume no liability for loss or damage incurred by following these suggestions. Seller warrants only that this product will meet the specifications set forth. Any other representation or warranty, either express or implied, is specifically disclaimed including warranties of fitness for a particular purpose and of merchantability. Sellers and manufacturers only obligation shall be to replace such quantity of the product proved to be defective. Before using, user shall determine the suitability of the product for users intended application and user assumes all risk and liability whatsoever in connection therewith. Neither seller nor manufacturer shall be liable in tort, contract or under any theory for any loss or damage, incidental or consequential, arising out of the use of or the inability to use the product.

**ECO2 Magnesia** | [www.eco2magnesia.ca](http://www.eco2magnesia.ca)  
 Kathleen Verret, ing., **ECO2 Project Director**  
 Phone: 418-271-5581 E-mail: [kv@eco2magnesia.ca](mailto:kv@eco2magnesia.ca)